

Fascia(US06) Technical Sheet

Model	Photo	Dimension
US06		138.4×15.0 mm (5.4×0.6 in)

NO.	Property	Test Method	Test results	Remark
1	Brinell hardness	EN15534	8.2N/mm ²	
2	Boiling test	EN15534	Water absorption in weight: 0.52%	
3	Bond Strength	EN319	Average Bond Strength>2.3MPa No obvious abruption and damage after test	
4	Coefficient Linear Thermal Expansion	ASTM D696	35.6×10 ⁻⁶ mm/mm °C	
		EN15534	34.0×10 ⁻⁶ K ⁻¹	
5	Degree of chalking	EN15534	Rating 0, no chalking	
6	Fire Resistance	ASTM E84	Flame Spread Index(FSI): 85 Smoke Developed Index(SDI): 300	
7	Formaldehyde Content	EN717-1	Non Detected	
		ASTM D6007-14	Non Detected	
8	Heavy Metal Content	EPA3051	Sb: ND, As: ND, Se: ND, Sn: ND	
9	Heat reversion	EN15534 EN479	0.11% (Test temperature: 100°C)	
10	Heat build-up	EN15534	ΔT=-3.1°C	

NO.	Property	Test Method	Test results	Remark
11	Lead Content Test	EUNo.628/2015	Non Detected	
12	Mould Resistance	ASTM G21	Rating 0	
13	Moisture Content	EN15534 EN322	0.78%	
14	Neutral salt spray test	ASTM B117-2011	After 200 hours tests, there was no visible change appeared on the surface: Front surface: $\Delta E^*=1.22$, Grey Scale: 4-5 Back surface: $\Delta E^*=1.06$, Grey Scale: 4-5	
		EN15534 ISO9227	$\Delta E^*=1.42$, Grey Scale=4 (Exposure 96h)	
15	Pb, Cd, Hg, Cr6+	RoHs-IEC62321	Pb: ND, Cd: ND, Hg: ND, Cr ⁶⁺ : ND	
16	Resistance to scratch test	ISO4586-2	Rate 2	
17	Resistance to artificial weathering	EN15534 ISO4892-2	After 2000h exposure $\Delta E^*=1.09$, Grey Scale=4-5	
18	Rockwell Hardness	ASTM D785	78.7R	
19	Swelling and water absorption (24hours immersion)	EN15534	①Swelling: 0.08% in thickness, 0.02% in width, 0.02% in length. ②Water absorption: 0.10%	
20	Swelling and water absorption (28days immersion)	EN15534	①Swelling: 0.62% in thickness, 0.04% in width, 0.06% in length. ②Water absorption: 0.25%	
21	SRI Testing	ASTM C1549, ASTM C1371, ASTM E1980	19	
22	Thermal Resistance	ASTM C518-2010	Thermal conductivity: 0.1589W/(m·k) Thermal resistance: 0.0830(m ² ·K)/W	
23	VOC&TVOC	ASTM D5116-11	Non Detected	
24	Water absorption	ASTM D1037-12B (24h)	Water absorption(24h): 0.11%	